

Customer No.: 31561
Application No: 10/707, 112
Docket NO.11761-US-PA

Claim Amendment

Please amend the claims according to the following listing of claims and substitute it for all prior versions and listings of claims in the application.

1. (currently amended) A method of fabricating a passivation layer, comprising the steps of:
- providing a substrate having a plurality of device structures and at least an interconnect thereon;
 - forming a patterned metallic layer over the interconnect;
 - performing a plasma-enhanced chemical vapor deposition process to form a first passivation layer over the metallic layer, wherein the plasma-enhanced chemical vapor deposition process is carried out at a processing pressure between about 9-21 to 25 Torrs and with a processing power between about 1 to 45 Watts; and
 - forming a moisture impermeable second passivation layer over the first passivation layer.
- Claim 2 (cancelled)
3. (original) The method of claim 1, wherein the first passivation layer comprises a silicon oxide layer.
4. (original) The method of claim 1, wherein the second passivation layer comprises a silicon nitride layer.

2 BEST AVAILABLE COPY

Customer No.: 31561
Application No: 10/707, 112
Docket NO.11761-US-PA

5. (currently amended) A method of fabricating a passivation layer, comprising the steps of:

providing a substrate having a plurality of device structures and at least an interconnect thereon;

forming a patterned metallic layer over the interconnect;

performing a semi-atmospheric chemical vapor deposition process with liquid tetra-ethyl-ortho-silicate (TEOS) and ozone inside a reaction chamber to form a first passivation layer over the metallic layer, wherein the liquid tetra-ethyl-ortho-silicate flowing into the reaction chamber has a flow rate between 500 sccm to 3000 sccm and the ozone flowing into the reaction chamber has a flow rate between 5000 sccm to 15000 sccm;
and

forming a moisture impermeable second passivation layer over the first passivation layer.

Claims 6-7 (cancelled)

8. (original) The method of claim 5, wherein the pressure inside the reaction chamber during the semi-atmospheric chemical vapor deposition process is between about 20 to 750 Torrs.

9. (original) The method of claim 5, wherein the semi-atmospheric chemical vapor deposition process is carried out at a temperature between about 200°C to 600°C.

Customer No.: 31561
Application No: 10/707, 112
Docket NO.11761-US-PA

10. (original) The method of claim 5, wherein the first passivation layer comprises a silicon oxide layer.

11. (original) The method of claim 5, wherein the second passivation layer comprises a silicon nitride layer.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.